

# **TEST REPORT**

Meridian Business Park, Leicester LE19 1WD, United Kingdom

Centre Court,

Tel: +44 (0) 116 263 0330 Fax: +44 (0) 116 263 0311/12

Web: www.intertek.com/consumergoods

**DATE**: 26<sup>th</sup> August 2011

NUMBER: LECH00323096

**APPLICANT:** Frogwill.com A. Wronski W.Wronski sp. j.

Lencewicza 3/34 01-493 Warsaw POLAND

For the attention of Pawel Wronski

**SAMPLE DESCRIPTION:** Findings, Earrings – Colour Silver

REFERENCE / STYLE NO.: 2519 Ear Wire with Ball and Coil 2cm

2543 Small Ear Wire 1.4cm

3037 Ear Wire with Ball and Coil 2cm 3058 Ear Wire with Ball and Loop 1.5cm

RETAILER: Not specified

**SAMPLES RECEIVED:** 3<sup>rd</sup> August 2011

PURCHASE ORDER: Not specified

**TEST REQUEST:** ^REACH Annex XVII item 27 (Nickel release)

**CONCLUSION:** The results of the tests carried out **MEET** the requirements of the requested

Regulation.

Tests marked (\*) in this Test Report are not included in the UKAS Accreditation Schedule for this Laboratory. Tests marked (^) in this Test Report have been sub-contracted to an agent approved by Intertek. Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.



**TEST REPORT** 

Centre Court, Meridian Business Park, Leicester LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330 Fax: +44 (0) 116 263 0311/12 Web: www.intertek.com/consumergoods

#### **NUMBER:** LECH00323096

### **NICKEL RELEASE TESTING ON COATED / PLATED ITEMS**

### **METHOD**

The samples were treated following the methods specified in EN12472 and EN1811. The determination of nickel present was by Flame AAS.

### **RESULTS**

# **TESTING WITHOUT WEAR AND CORROSION**

COMPONENT IDENTITY	SAMPLE AREA (cm²)	VOLUME OF TEST SOLUTION (mL)	ADJUSTED NICKEL RELEASE (µg/cm²/week)	RESULT
2543 Ear Wire	1.3	5	<0.02	Pass
2519 Ear Wire	2.0	5	<0.02	Pass
2519 Ball	0.3	5	<0.02	Pass
2519 Spring	0.3	5	<0.02	Pass
3058 Ear Wire	2.0	5	<0.02	Pass
3058 Spring	0.3	5	<0.02	Pass
3037 Ear Wire	1.8	5	<0.02	Pass
3037 Ball	0.3	5	0.03	Pass
3037 Spring	0.2	5	0.03	Pass

#### TESTING WITH WEAR AND CORROSION

COMPONENT IDENTITY	SAMPLE AREA (cm²)	VOLUME OF TEST SOLUTION (mL)	ADJUSTED NICKEL RELEASE (µg/cm²/week)	RESULT
2543 Ear Wire	1.3	5	<0.02	Pass
2519 Ear Wire	2.0	5	<0.02	Pass
2519 Ball	0.3	5	<0.02	Pass
2519 Spring	0.3	5	<0.02	Pass
3058 Ear Wire	2.0	5	<0.02	Pass
3058 Spring	0.3	5	<0.02	Pass
3037 Ear Wire	1.8	5	<0.02	Pass
3037 Ball	0.3	5	<0.02	Pass
3037 Spring	0.2	5	0.03	Pass

Nickel release results given as µg/cm²/week

The limit specified is 0.5 µg/cm²/week

(For post assemblies which are inserted into pierced parts of the human body, a lower limit of

PAGE 2 OF 3



# **TEST REPORT**

**NUMBER:** LECH00323096

0.2µg/cm²/week applies)

24<sup>th</sup> August 2011 Date of testing:

Centre Court, Meridian Business Park, Leicester LE19 1WD, United Kingdom

Tel: +44 (0) 116 263 0330 Fax: +44 (0) 116 263 0311/12 Web: www.intertek.com/consumergoods



**END OF REPORT**